

XEVA-8LB-58°

LDPE and EVA Crosslink Foam

Property	Specification	Tolerance	Unit	Method
Hardness	58° (79°F)	+/- 5°	Shore C	EVA-IT-LAB-05
Density	8.0	+/- 1	lb/ft3	ASTM D3575
Tensile Strength	148.78	MIN	lb/in2	ASTM D3575
Tear Strength	36.94	MIN	lb/in	ASTM D3575
Elongation	106	+/- 15	%	ASTM D3575
Shrinkage	3.93	MAX	%	ASTM D3575
Contraction	2.5 158° F	MAX	%	EVA-IT-LAB-11
Dilation	2.5 41° F	MAX	%	EVA-IT-LAB-11
Compression set	10	MAX	%	EVA-IT-LAB-01

Available Sizes

	Mold	Texture	Thickness	Unit	Width	Unit	Length	Unit
Option 1	114-18T	N/A	1.34	Inches	43.31	Inches	86.61	Inches
Option 2	114-21T	N/A	1.57	Inches	43.31	Inches	86.61	Inches
Option 3	114-25T	N/A	1.73	Inches	43.31	Inches	86.61	Inches
Option 4	RMX5-27.5T	N/A	1.97	Inches	49.61	Inches	108.27	Inches
Option 5	G126-7/9/14T	Bubble	0.47, 0.71, 1.10	Inches	47.24	Inches	84.65	Inches
Option 6	G127-9/14T	Peanut	0.71, 1.10	Inches	45.28	Inches	82.68	Inches
Option 7	132-9T	Puma	0.71	Inches	47.24	Inches	84.65	Inches

Thickness Tolerances:

Complete bun +/- 0.04".
Half Bun +/- 0.02"
Below half bun +/- 0.012"

Width and Length Tolerances:

Without texture +/- 0.79".
With Texture +/- 1.97"

Visual Attributes

EVA and LDPE Crosslinked foam is a material that goes through an intense expansion process. In which it is very common to have some defects in the material, such as pinhole, bubble marks or skin marks. However, the bun must have a yield of at least 95%.

Note: It's recommended to cut the material at a temperature between 68°F to 86°F.

Evacolors Industrial S.A. de C.V. Carr. San Francisco - León N° 3304
Int. 7 Col. Buena Vista C.P. 36340, San Francisco del Rincón, Guanajuato. México